



Technical Data Sheet

DOWSIL™ SE 4402 Thermally Conductive Adhesive

DOWSIL™ SE 4402 Thermally Conductive Adhesive is a one-part, gray, flowable thermally conductive adhesive.

Features & Benefits

- One part material – no mixing
- Long working time
- Heat curable
- Flowable
- Good adhesion
- Thermally conductive – removes heat from sensitive components

Composition

- Thermally conductive filler
- Polydimethylsiloxane adhesive

Applications

- Designed to provide long term bonding and efficient thermal flow
- Typical applications are bonding organic and ceramic substrates to heat sinks for control modules in Automotive

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
One part or Two part		One
Color		Gray
Fluidity	mm	65
Viscosity	cP	32,000
	mPa-sec	32,000
	Pa-sec	32
Heat Cure time at 150°C	minutes	30
Specific Gravity (cured)		2.2
Durometer Shore A		75

UNRESTRICTED – May be shared with anyone

®™ The DOW Diamond and DOWSIL are trademarks of The Dow Chemical Company

DOWSIL™ SE 4402 Thermally Conductive Adhesive

© 2017 The Dow Chemical Company. All rights reserved.

Typical Properties (Cont.)

Property	Unit	Result
Tensile Strength	psi	800
	MPa	5.5
	kg/cm ²	56.4
Elongation	%	115
Unprimed Adhesion - Lap Shear (Al)	psi	530
	MPa	3.65
	N/cm ²	365
Dielectric Constant at 1 MHz		4.8
Dissipation Factor at 1 MHz		0.003
Dielectric Strength	volts/mil	625
	kV/mm	25
Volume Resistivity	ohm-cm	3E+15
Thermal Conductivity	btu/hr-ft-°F	0.52
	W/mK	0.9

Description

The heat-cure, thermally conductive adhesives produce no by-products in the cure process, allowing their use in deep section and complete confinement. These adhesives will develop good, primerless adhesion to a variety of common substrates including metals, ceramics, epoxy laminate boards, reactive materials and filled plastics. PCB system assemblies are continually designed to deliver higher performance. Especially in the area of consumer devices, there is also a continual trend towards smaller, more compact designs. In combination these factors typically mean that more heat is generated in the device. Thermal management of PCB system assemblies is a primary concern of design engineers. A cooler device allows for more efficient operation and better reliability over the life of the device. As such, thermally conductive compounds play an integral role here. Thermally conductive materials act as a thermal "bridge" to remove heat from a heat source (device) to the ambient via a heat transfer media (i.e. heat sink). These materials have properties such as low thermal resistance, high thermal conductivity, and can achieve thin Bond Line Thicknesses (BLTs) which can help to improve the transfer of heat away from the device.

Substrate Testing

To ensure maximum bond strength for adhesives on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength test is needed. This ensures compatibility of the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or to detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.

UNRESTRICTED – May be shared with anyone

®™ The DOW Diamond and DOWSIL are trademarks of The Dow Chemical Company

DOWSIL™ SE 4402 Thermally Conductive Adhesive

© 2017 The Dow Chemical Company. All rights reserved.

Processing/Curing	<p>Addition-cure adhesives should be cured at 100°C (212°F) or above. The cure rate is rapidly accelerated with heat (see heat-cure times in Typical Properties table). Thin sections of less than 20 mils may be cured in 15 minutes at 150°C (30°F). For thicker sections, a pre-cure at 70°C (158°F) may be necessary to reduce voids in the elastomer. Length of pre-cure will depend on section thickness and confinement of adhesive. It is recommended that 30 minutes at 70°C (158°F) be used as a starting point for determining necessary pre-cure time. Addition-curing materials contain all the ingredients needed for cure with no by-products from the cure mechanism. Deep-section or confined cures are possible. Cure progresses evenly throughout the material. These adhesives generally have long working times.</p>
Adhesion	<p>Dow silicone adhesives are specially formulated to provide unprimed adhesion to many reactive metals, ceramics and glass, as well as to selected laminates, resins and plastics. However, good adhesion cannot be expected on non-reactive metal substrates or non-reactive plastic surfaces such as Teflon®, polyethylene or polypropylene. Special surface treatments such as chemical etching or plasma treatment can sometimes provide a reactive surface and promote adhesion to these types of substrates. Dow primers can be used to increase the chemical activity on difficult substrates. For best results, the primer should be applied in a very thin, uniform coating and then wiped off after application. After application, primers should be thoroughly cured prior to application of the silicone elastomer. Poor adhesion can be experienced on plastic or rubber substrates that are highly plasticized, since the mobile plasticizers act as release agents. Small-scale laboratory evaluation of all substrates is recommended before production trials are made. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion.</p>
Useful Temperature Ranges	<p>For most uses, silicone adhesives should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible for most products, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicones is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.</p>
Solvent Exposure	<p>In general, the product is resistance to minimal or intermittent solvent exposure, however best practice is to avoid solvent exposure altogether</p>
Usable Life And Storage	<p>The product should be stored in its original packaging with the cover tightly attached to avoid any contamination. Store in accordance with any special instructions listed on the product label. The product should be used by the indicated Exp. Date found on the label.</p>

UNRESTRICTED – May be shared with anyone

®™ The DOW Diamond and DOWSIL are trademarks of The Dow Chemical Company

DOWSIL™ SE 4402 Thermally Conductive Adhesive

© 2017 The Dow Chemical Company. All rights reserved.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

How Can We Help You Today?

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge, and processing experience to work for you.

For more information about our materials and capabilities, visit www.consumer.dow.com.

To discuss how we could work together to meet your specific needs, go to www.consumer.dow.com for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

Teflon is a registered trademarks of E. I. du Pont de Nemours and Company or its affiliates

<http://www.consumer.dow.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

