



LOCTITE® ECCOBOND UF 3711

January 2025

PRODUCT DESCRIPTION

LOCTITE® ECCOBOND UF 3711 provides the following product characteristics:

Technology	Epoxy
Appearance	White paste
Components	One component
Product benefits	• UV curable • Thixotropic • Very low CTE • High Tg and modulus • Low curing shrinkage
Cure	UV or UV + heat cure
Application	Edgebond, Encapsulation, Active alignment
Operating temperature range	(-40°C to 125°C)

LOCTITE® ECCOBOND UF 3711 curable adhesive is formulated for chips to enhance the reliability performance. It provides a uniform and void-free encapsulant edgebond, maximizing the device's temperature cycling capability, distributing stress away from solder connects, as well as improving device's reliability under high temperatures and high humidity.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, TA Rheometer, 20mm 0°cone, 25°C, mPa.s (cP)	
@15s ⁻¹	35,000
TI (1.5s ⁻¹ /15s ⁻¹)	4.6
Specific gravity @ 25°C, g/cc	1.78
Work life, hours	72
Shelf life @ -20°C, days	365

TYPICAL CURING PERFORMANCE

Recommended UV cure condition

Light source and condition:	
365nm UV LED lamp	
UV wavelength, nm	365
Light intensity, mW/cm²	700
UV energy, mJ/cm²	7,000

LOCTITE® ECCOBOND UF 3711 can be cured by exposure to UV light of sufficient intensity. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of light source, exposure time and light transmittance of the substrate through which the light must pass.

For application where there is shadow area or high curing depth (≥4mm) is required, secondly heat cure is recommended following UV irradiation. Recommended secondary heat cure conditions are:

Option 1	
Temperature, °C	120
Time, min	≥10
Option 2	
Temperature, °C	100
Time, min	≥20
Option 3	
Temperature, °C	80
Time, min	≥40

TYPICAL PROPERTIES OF CURED MATERIAL

Sample cured by UV irradiation (365 nm, 700 mW/cm² and 7000 mJ/cm²)	
Physical properties	
Coefficient of thermal expansion, ASTM E831-86, µm/m/K:	
alpha 1	20
alpha 2	62
Glass transition temperature, Tg by TMA, °C	150
Tensile modulus, @ 25°C by DMA, GPa	13.6
Cure shrinkage, Volume, %	1.4
Water absorption, (168h, 85°C85%RH), %	1.1

Electrical properties	
Dielectric constant / Dissipation factor	
@ 5 GHz	3.3 / 0.0108
Volume resistivity, @ 500 volts, ohms-cm	2.91×10 ¹⁵
Dielectric breakdown strength, KV/mm	24

TYPICAL PERFORMANCE OF CURED MATERIAL

Die shear strength	
3*3 glass die to FR4	kgf >12
	psi >1,740

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet (SDS).



Directions for use

1. Set the syringe to stand vertically at room temperature, thaw the adhesive to 25°C.
2. Thawed adhesive should be immediately placed on dispense equipment for use.
3. If the adhesive is transferred to a final dispensing reservoir, additional SOP need to be generated to avoid entrapment of contaminants, moisture and air into the adhesive.
4. Adhesive must be completely used within the product's recommended work life.
5. Do not re-freeze/re-use any thawed adhesive.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: -20°C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2