

LOCTITE STYCAST PC 18M

September 2012

PRODUCT DESCRIPTION

LOCTITE STYCAST PC 18M provides the following product characteristics:

Technology	Urethane
Appearance	Clear amber
Product Benefits	<ul style="list-style-type: none"> • Reworkable • Solvent resistant • Room temperature cure • Resistance to discoloration • Fluorescent under UV light • No cracking or crazing with vibration • Superior toughness and abrasion resistance • Provides environmental and moisture protection
Operating Temperature - Continuous	up to 110°C
Cure	Heat cure and Room temperature cure
Application	Conformal coating
Typical Assembly Applications	Printed circuit board coating

LOCTITE STYCAST PC 18M is a solvent based one component urethane coating which may be cured at room temperature. This material retains its light color after long exposure to elements.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Free TDI content, %	<1
NCO content, %	4.0
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 2, speed 20 rpm	350
Solids Content by weight, %	50
Specific Gravity @ 25°C	1.01
Shelf Life , Unopened @ 25°C (from date of manufacture), days	548
Flash Point , °C	32

TYPICAL CURING PERFORMANCE

Cure Schedule

Boards must be air-dried 30 to 45 minutes prior to curing
2 hours @ 60°C , in an oven

Alternative Cure Schedule

Air Dry @ room temperature, @ average relative humidity of 30 to 50%:

Tack-free, hours	1 to 4
Semi-hard film, days	1
Optimum properties, days	7

Place an open container of distilled water in the oven if relative humidity is below 30% and allow to equilibrate at 60°C prior to placing the coated parts in the oven.

Drying of the coating depends upon solvent evaporation. For optimum performance, boards should be dried at least 30 minutes at 25°C to remove solvents before final drying in oven (or before applying additional coats).

Drying and curing of the coating depends upon evaporation of the solvent and subsequent reaction of the polymer with moisture in the air at elevated or room temperature. Optimum physical and electrical properties can be obtained with room temperature cure but moisture must be present in the air, at a minimum relative humidity level of 30 %.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Extractable Ionic Content, :	
Chloride (Cl-)	38
Sulfate (SO ₄ ²⁻)	10
Phosphate (PO ₄)	28
Nitrate (NO ₃)	5
Nitrogen Dioxide (NO ₂)	N/D
Bromine (Br)	N/D

Electrical Properties

Insulation Resistance , ohms (1 to 3 mil film):	
Cycle 1 25°C/50% R.H.	1×10 ¹⁵
Cycle 4 65°C/95% R.H.	4×10 ¹⁰
Cycle 7 65°C/95% R.H.	5×10 ¹⁰
Cycle 10 65°C/95% R.H.	2×10 ¹⁰
24hours after Cycle 10 25°C/50% R.H.	2×10 ¹³
Leakage Rate:	
Before thermal shock, microamperes	<10
After thermal shock, microamperes	<10
Dielectric Withstand at 1,500volts, 50Hz:	
Before thermal shock and moisture exposure	Pass
After thermal shock and moisture exposure	Pass
Dielectric Constant @ 25°C :	
@ 100KHz	4.2
Dissipation Factor @ 25°C:	
@ 100KHz	0.01
Volume Resistivity, ohms-cm	2×10 ¹³
Dielectric Strength, volts/mil	1,200

TYPICAL ENVIRONMENTAL RESISTANCE**Miscellaneous**

Fungus Resistance per ASTM G21	Non nutrient
Appearance of film (after thermal and moisture resistance testing):	
Blistering	None
Wrinkling	None
Cracking	None
Peeling	None
Discoloration	None
Flexibility:	
Cracking over diameter mandrel	None

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

If material was stored below 23°C, it MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Printed circuits or other objects to be coated should be cleaned in accordance with accepted industry practices. Isopropyl alcohol, or methyl ethyl ketone have been found satisfactory as cleaning agents. If activated flux residues are present, appropriate detergents may be needed to remove any residue.

Application:

1. Moisture may cause polymerization. Contents may solidify. If this occurs, warm to 49°C until clear and thoroughly mix before using.
2. Apply by brush, dip or spray for a 1 to 2mil film.

Viscosity:

1. Viscosity may be reduced when desired with LOCTITE STYCAST AC 0305 thinner.
2. Other solvents such as methoxy propyl acetate, methyl ethyl ketone, xylene and toluene can be used alone or as a mixture depending on how coating will be applied and drying time desired.
3. Dilutions of 15 to 20 % will generally be sufficient for most applications.

Cleaning

1. Uncured LOCTITE STYCAST PC 18M may be cleaned up with ketones or the solvents listed above.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : ≤23 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb/F
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1