

ALPHA[®] SACX PLUS[®] 0107 / SACX PLUS 0100

Lead Free Wave Solder Metal

DESCRIPTION

ALPHA SACX Plus 0107 is a next generation lead-free alloy suitable for use as a replacement for SnPb and SAC alloys in wave solder and lead tinning process. The **SACX Plus 0100** variant is used to stabilize / reduce the copper content in the wave solder bath, this requirement will depend on process conditions. As with all Alpha Metals bar solder, Alpha's proprietary Vaculoy alloying process is used to remove certain impurities, particularly oxides. The product is further enhanced with the addition of 3 minor elements to reduce dross formation, improve the joint cosmetics and hole fill.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES & BENEFITS

Features:

- YIELD FR2 boards – Comparable to original SACX 0307, superior performance for bridging compared to Sn99.3/Cu0.7/Ni based alloys
- PRICE – Lower unit price due to reduction in Silver content
- DROSS GENERATION – Equivalent to original SACX 0307
- COPPER DISSOLUTION – Equivalent to original SACX 0307

Benefits:

- Lowers Total Cost of Ownership due to the lower material cost, high yields and low dross generation, suited for FR2 assemblies
- Gives very good solderability due to the fast wetting speed
- Gives very good drainage and hence lower levels of bridges due to the formulation containing Silver
- Delivers good performance across a range of flux technologies

The proprietary Vaculoy process is a highly effective method for removing included oxides from solder. This is extremely important because included oxides generate excessive drossing and increase the viscosity of the solder. Solder with higher viscosity can result in increased soldering defects (i.e., solder bridging).

APPLICATION GUIDELINES

ALPHA SACX Plus 0107 is suitable for wave soldering and selective soldering for electronic assemblers interested in implementing a lead-free process. It is suited to single side boards. A solder pot temperature of 255 to 265 °C (491 to 509 °F) is recommended with a contact time 2.3 to 3.5 seconds. For suitable wave solder fluxes, contact your local sales representative. Lead free Reclaim services including dedicated lead-free containers are also available; please consult your local Alpha sales office.

AVAILABILITY

ALPHA SACX Plus 0107 is available in 1kg (2.2lb) bar, chunks, Feeder Ingots and Autofeed Wire.

TECHNICAL SPECIFICATION

A 0.10% of Lead (Pb) complies with all requirements of RoHS Directive 2015/863/EU. Alloy specification for maximum Lead (Pb) Content = 0.07%. SACX Plus 0107 is also available in an Ultra-Low Lead (ULL) version which contains a maximum of 0.05% Pb. All alloy properties remain the same for SACX Plus 0107 ULL.

Material Property	Units	SACX Plus 0107
Solidus	Celsius	217
Liquidus	Celsius	228
Silver Content	%	0.1 + 0.02 +/-0.02
Copper Content	%	0.70 +/-0.1
Lead Content	%	Max 0.07%

RECOMMENDED WAVE PROCESSING SETTINGS

Wave Configuration	Process Parameter	Suggested Process Settings
Single Wave	Pot temperature	255 to 265 °C (491 to 509 °F)
	Conveyor speed	1.0 to 1.5 m/min (3.3 to 5 ft/min)
	Contact time	2.3 to 2.8 seconds
	Wave Height	1/2 to 2/3 of board thickness
	Dross removal	Once per 8 hour run time
	Copper Check	Every 8,000 boards until 40,000
Dual Wave	Pot temperature	255 to 265 °C (491 to 509 °F)
	Conveyor speed	1.0 to 1.5 m/min (3.3 to 5 ft/min)
	Contact time	3.0 to 3.5 seconds
	Wave Height	1/2 to 2/3 of board thickness
	Dross removal	Once per 8 hour run time
	Copper Check	Every 8,000 boards until 40,000

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams. Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

www.macdermidalpha.com

North America 140 Centennial Avenue Piscataway, NJ 08854 1.800.367.5460	Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400	Asia 8/F., Two Sky Parc 51 Hung To Road Kwun Tong, Kowloon, Hong Kong, SAR China 852.2500.5365
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.