

LOCTITE® ABLESTIK ABP 8068TH

October 2024

PRODUCT DESCRIPTION

LOCTITE® ABLESTIK ABP 8068TH provides the following product characteristics:

Technology	Silver Pressure-less Sintering
Chemical type	Epoxy
Appearance	Silver
Filler type	Silver
Product benefits	<ul style="list-style-type: none"> • One component • Excellent dispensing stability • Compatible with bended needle • Excellent RBO control • Long open time • High thermal conductivity • Low stress • Robust reliability
Cure	Heat cure
Application	Conductive die attach paste, Electronic adhesives & solder, Semiconductor paste
Typical package application	LGA, QFN, SOP, LED
Key substrates	ENEPIG/ENIG substrate, Cu, Ag, PPF leadframe

LOCTITE® ABLESTIK ABP 8068TH is a die attach paste based on silver pressure-less sintering technology for semiconductor package to meet high thermal/electrical requirements. It has enhanced sintering performance and thermal conductivity, improved resin bleed performance comparing with ABP 8068TB. It is formulated with high thermal conductivity to meet thermal dissipation requirement, and the unique sintering system enables excellent workability as well as good stress control to achieve robust reliability performance.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield CP51, 25°C, mPa.s (cP)	
Speed 5 rpm	13,500
Thixotropic index, (0.5/5 rpm)	5.3
Work life @ 25°C, hours	24
Shelf life @ -40°C, days	365

TYPICAL CURING PERFORMANCE

Recommended cure schedule

For the die size ≤ 3 x 3 mm
5°C/mins ramp from 25°C to 150°C, hold for 30-60 minutes
5°C/mins ramp to 200°C, hold for 90-120 minutes, N2 oven

For the die size > 3 x 3 mm
5°C/mins ramp from 25°C to 150°C, hold for 30-90 minutes
5°C/mins ramp to 200°C, hold for 90-120 minutes, N2 oven

Weight loss on cure

Weight loss on cure, %	9.4
------------------------	-----

The above cure profile(s) are guideline recommendations. These cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical properties

Coefficient of thermal expansion, TMA expansion (ppm/°C):	
Below Tg	26
Above Tg	47
Glass transition temperature, TMA penetration, °C	8.7
Storage modulus, DMTA, GPa	
@ -65°C	16.5
@ 25°C	13.3
@ 150°C	4.9
@ 250°C	3.9
Tan DELTA, DMTA, °C	121.3
Extractable ionic content, ppm	
Sodium (Na+)	<10
Potassium (K+)	<10
Chloride (Cl-)	<20
Bulk thermal conductivity, W/(m·K)	150
Volume resistivity, ohm·cm	9.9 x 10 ⁻⁶
Moisture absorption @ saturation, wt. %, @ 85°C/85% RH	0.075

Adhesion properties


Die shear strength, kg/f	
1 x 1 mm Au BSM die on Cu LF	
@ RT	3.5
@ 260°C	2.4
1 x 1 mm Au BSM die on Ag LF	
@ RT	4.8
@ 260°C	2.3
1 x 1 mm Au BSM die on PPF LF	
@ RT	4.9
@ 260°C	2.5
3 x 3 mm Ag BSM die on Ag LF	
@ 260°C	25.0
5 x 5 mm Ag BSM die on Ag LF	
@ 260°C	48.0

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

Thawing

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. Thaw times depend on the syringe size.
4. Consult handling guide for more information.
5. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
6. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.

**Direction for use**

1. Thawed material should immediately be placed on dispense equipment for use.
2. If the adhesive is transferred to a final dispensing reservoir, care must be exercised to avoid entrapment of contaminants and/or air into the adhesive.
3. Adhesive must be completely used within the product's recommended work life.
4. Alternate dispense amounts may be used depending on the application requirements.
5. Star or crossed shaped dispense patterns will yield fewer bondline voids than the matrix style of dispense pattern.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40°C. Storage below -40°C or greater than -40°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1