

LOCTITE® ABLESTIK ABP 8900NC-1B1

November 2023

PRODUCT DESCRIPTION

LOCTITE® ABLESTIK ABP 8900NC-1B1 provides the following product characteristics:

Technology	Epoxy
Appearance	Yellow
Filler type	PTFE
Cure	Heat cure; Snap cure
Product benefits	• Fast cure • Snap curable • High strength • Controlled bondline thickness • Non-conductive • Low resin bleed • Moderate stress absorbing • Excellent dispensability, minimal tailing and stringing
Application	Semiconductor pastes; Non-conductive die attach paste
Key substrates	Bare copper, Ag plated Cu leadframes; Pd plated Cu leadframes

LOCTITE® ABLESTIK ABP 8900NC-1B1 is designed for high throughput die attach applications. It is specially designed for use in small to medium package sizes.

LOCTITE® ABLESTIK ABP 8900NC-1B1 is formulated with spacers close to 20 to 25 µm. It is the spacer control version of LOCTITE® ABLESTIK 8900NC. Actual performance will depend on die size, aspect ratio and package design.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield CP51 @ 25°C, mPa·s (cP)	
Speed 5 rpm	12,500
Thixotropic index, (0.5/5 rpm)	5.9
Work life @ 25°C, hours	24
Shelf life @ -40°C, days	365

TYPICAL CURING PERFORMANCE

Weight loss on cure

Weight loss on cure, %	2.1
------------------------	-----

Recommended cure condition

30-minute ramp to 175°C + 15 minutes @ 175°C

Snap cure schedule

Zone No.	1	2	3	4	5	6	7	Time
Temp, °C	160	165	200	200	220	220	220	1-2 min

Note: N₂ flow: 15 liters/minute

N₂ Preheat temp: 150°C

The above cure profile are guideline recommendations. These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coefficient of thermal expansion, TMA	
Below Tg, ppm/°C	65
Above Tg, ppm/°C	162
Glass transition temperature, TMA, °C	19
Tensile modulus, DMTA	
@ 25°C, N/mm ²	1,310
@ 150°C, N/mm ²	117
@ 250°C, N/mm ²	62
Extractable ionic content, @100°C for 24hours	
Chloride (Cl-), ppm	≤20
Sodium (Na+), ppm	≤10
Potassium (K+)	≤10
Water extract conductivity, µmhos/cm	105
Weight loss @ 300°C, %	1.58

Thermal properties

Thermal conductivity, W/(m·K)	0.3
-------------------------------	-----

Electrical properties

Volume resistivity, ohm-cm	2.3x10 ¹³
----------------------------	----------------------

Adhesion properties

Die Shear Strength

2 x 2 mm Si Die @ 25°C, kg-f

Substrate	
on Ag/Cu leadframe	13.0
on Cu leadframe	12.5
on Alloy 42 leadframe	13.8
on Ni/Pd leadframe	13.0
on Au/Flash leadframe	12.1

7.5 x 7.5 mm Si Die @ 250°C, kg-f

Substrate	Post cure	Post mold	24 hrs @ 85%/85% RH
Ag/Cu LF	8.1	10.9	3.2
Cu LF	4.2	3.3	4.0
Alloy 42 LF	12.0	11.2	5.1
Ni/Pd LF	3.4	9.4	2.8

12.5 x 12.5 mm Si Die @ 250°C, kg-f

Substrate	Post cure	Post mold	24 hrs @ 85%/85% RH
Ag/Cu LF	20.4	14.8	11.3
Cu LF	30.6	17.5	11.3
Alloy 42 LF	29.1	30.0	13.8
Ni/Pd LF	3.8	14.4	2.7

Die Shear Strength vs. Temperature

3 x 3 mm Si Die, kg-f

Substrate	@ RT	@ 200°C	@ 250°C
Ag/Cu LF	24.1	2.9	2.5
Cu LF	22.2	2.7	1.4
Alloy 42 LF	25	2.4	1.4
Ni/Pd LF	22.3	1.9	1.5
Au/Flash LF	21.8	1.7	1.0

Chip Warpage

7.5 x 7.5 mm Si Die, µm

Substrate	Post cure	Post mold bake (4 hrs @ 175°C)
Ag/Cu LF	9.6	10.1
Cu LF	10.9	10.6
Alloy 42 LF	3.5	1.3
Ni/Pd LF	10.5	9.9

12.5 x 12.5 mm Si Die, µm

Substrate	Post cure	Post mold
Ag/Cu LF	46.7	47.9
Cu LF	45.4	46.8
Alloy 42 LF	5.4	3.8
Ni/Pd LF	45.9	47.4

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

Thawing:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
4. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.

Direction for use

1. Thawed material should immediately be placed on dispense equipment for use.
2. If the adhesive is transferred to a final dispensing reservoir, care must be exercised to avoid entrapment of contaminants and/or air into the adhesive.
3. Adhesive must be completely used within the product's recommended work life.
4. Silver-resin separation may occur if the adhesive is left out at room temperature, beyond the recommended work life.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40°C. Storage below -40°C or greater than -40°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$



Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office."

Reference 1