

LOCTITE ABLESTIK EMI 8660S

February 2018

PRODUCT DESCRIPTION

LOCTITE ABLESTIK EMI 8660S provides the following product characteristics:

Technology	Coating, Silver Sintering
Appearance	Silver liquid
Cure	Heat cure
Application	Semiconductor, Coating
Filler Type	Silver
Product Benefits	• High electrical conductivity • High thermal conductivity • Sprayable • Good workability • Long work life • Excellent adhesion on mold compound and epoxy surfaces • Excellent adhesion to copper, gold and silver
Typical Applications	• Radio frequency (RF) • Wireless components • Memory • Sensors • Other sensitive devices
Application Method	Spraying, printing, dispensing

LOCTITE ABLESTIK EMI 8660S is an electrically conductive adhesive designed to achieve robust electromagnetic interference (EMI) shielding performance with extremely thin coating thickness at a single micrometer level for package level shielding applications.

The material has robust adhesion to mold compound, epoxy, copper, gold and silver surfaces.

When spray-coated, this material can be atomized to highly fine droplets for excellent uniformity at low to high coating thicknesses which can be controlled by equipment parameters.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield, 25 °C, mPa·s (cP):	
Spindle 18, Speed 5 rpm	340
Thixotropic Index (0.5/5 rpm)	3.0
Work Life @ 25°C, hours	24
Flash Point - See SDS	

TYPICAL DRYING PERFORMANCE

Recommended Curing Conditions

60 minutes @ 175°C

Oven atmosphere must be air, no ramp up.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Adhesion, ASTM D3359

After Cure:

Mold Compound	5B
Copper	5B
Silver	5B
Gold	5B

After MSL 3 Conditioning:

Mold Compound	5B
Copper	5B
Silver	5B
Gold	5B

Weight Loss @ 250°C, %	13
Extractable Ionic Content @ 100 °C, ppm:	
Chloride (Cl-)	<0.5
Sodium (Na+)	4
Potassium (K+)	1

Electrical Properties

Volume Resistivity, ohm-cm	1.00×10 ⁻⁵
Shielding performance @ 5 µm coating thickness, dB:	
@ 2.6 to 3 GHz	83
@ 3 to 4 GHz	78

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

- Allow container to reach room temperature before use
- After removing from the freezer, set the syringes to stand vertically while thawing
- DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the warmed up container should be removed prior to opening the container
- DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen

DIRECTIONS FOR USE

1. No special surface treatment is needed for the substrate surface before applying this material.
2. Before applying the material, it is recommended that the substrate is handled with care to prevent any organic contamination and/or residue.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -40 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

CLEAN-UP

The material can be cleaned with esters (butylacetate, ethylacetate) or ketones (MEK).

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion

herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1