

LOCTITE[®] HHD 3547BK

November 2020

PRODUCT DESCRIPTION

LOCTITE[®] HHD 3547BK provides the following product characteristics:

Technology	Polyurethane Hot Melt
Appearance	Black
Solids Content, %	100
Odour	Slight
Components	One part - requires no mixing
Cure	Solidification and Moisture
Application	Structural adhesive, Electronic device assembly

LOCTITE[®] HHD 3547BK is a reactive hotmelt adhesive based on polyurethane prepolymers. This material is designed to provide high initial strength after application. It is suitable for use in automatic or manual assembly processes.

LOCTITE[®] HHD 3547BK is not frost sensitive.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - Thermosel, 110 °C, mPa·s (cP):

Spindle 27, speed 20 min⁻¹ 5,000

Density @ 25°C ±0.05, g/cm³ 1.1

TYPICAL CURING PERFORMANCE

Open Time, approx. , minutes 3

Preheating Schedule 20 to 30 mins @ 110°C

Application Temperature, °C 100 to 110

Open time is the bonding range of a 1 mm bead of molten adhesive on substrate. It is based on room temperature environment. Higher temperature will lengthen the open time while lower environmental temperatures will shorten the open time.

LOCTITE[®] HHD 3547BK cures exclusively by moisture and gains its final strength in 1-5 days. This material, however, exhibits high handling strength instantly after bonding.

Curing is a chemical reaction depending on the following parameters:

- Humidity in the rooms of application and storage
- Moisture content on the substrates
- Permeability of the substrates to be bonded
- Application volume / layer of the adhesive film

The above cure profile(s) are guideline recommendation(s). These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Elongation, at break, %	655
Tensile Strength	N/mm ² >8 (psi) (>1,160)
Tensile Modulus	N/mm ² 130 (psi) (18,900)

Adhesive Properties:

Tensile Strength:	
PCGF to Ink Glass:	
After 1 hour	N/mm ² ≥2 (psi) (≥290)
After 24 hours	N/mm ² ≥6 (psi) (≥870)

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with chlorine or other strong oxidizing materials unless otherwise specifically stated.

Pretreatment:

1. The bonding surfaces must be clean, dry and free of oil and grease.
2. Substrate temperature should not fall below 20°C during application.
3. Lower temperatures will lead to early solidification of the adhesive and to a reduced open time, the adhesive might even flake off.
4. The substrates may be preheated if necessary.

Application:

1. LOCTITE® HHD 3547BK can be applied from heating cartridge guns, from usual syringe type melting equipment.
2. At longer rest periods, melting and application temperatures should be decreased. Longer exposure to higher temperatures can lead to a viscosity increase.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 to 28°C. Storage below 8°C or above 28°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1