

LOCTITE HHD 8150NS

July 2022

PRODUCT DESCRIPTION

LOCTITE HHD 8150NS provides the following product characteristics:

Technology	Methacrylate
Appearance - Part A	Yellow
Appearance - Part B	Blue
Appearance - Mixed	Green
Mix Ratio by volume, Part A:Part B	10 : 1
Cure	Room temperature cure after mixing
Product Benefits	<ul style="list-style-type: none"> Fast cure High strength
Application	Device assembly, Structural bonding
Typical Assembly Applications	<ul style="list-style-type: none"> Laptop cover Hand held devices Consumer electronic enclosure bonding
Key Substrates	<ul style="list-style-type: none"> Magnesium Aluminum alloys Anodized Aluminum PC and PC/ABS blends

LOCTITE HHD 8150NS two component methacrylate adhesive system is designed for use in handheld device cover assembly applications. This material reacts when mixed and is fully cured at room temperature.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Viscosity, Brookfield - RTV, 25 °C, mPa·s (cP)	50,000
Specific Gravity @ 25°C	0.98
Flash Point - See SDS	

Part B Properties (Isocyanate)

Viscosity, Brookfield - RTV, 25 °C, mPa·s (cP)	42,090
Specific Gravity @ 25°C	1.2
Flash Point - See SDS	

Mixed Properties

Specific Gravity @ 25 °C	0.99
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Open Time, minutes	5 to 6
--------------------	--------

LOCTITE HHD 8150NS is cured after mixing at room temperature.

Cure speeds may vary based on adhesive and substrate temperatures. Reference the peak exotherm and open times on this datasheet as a guide to better understand curing time trends.

After the fixture time is achieved the material usually has reached handling strength. For heavy parts handling strength can take longer.

Parts should be fixed for a minimum period of 24 hours prior to applying a load.

TYPICAL PROPERTIES OF CURED MATERIAL

Sample cured 24 hours @ 22°C

Physical Properties

Hardness, Shore D	72
Volumetric Shrinkage, %	11.5
Glass Transition Temperature, °C	71
Coefficient of Thermal Expansion :	
Below Tg, K ⁻¹	100×10 ⁻⁰⁶
Above Tg, K ⁻¹	100×10 ⁻⁰⁶

TYPICAL PERFORMANCE OF CURED MATERIAL

Sample cured 24 hours @ 22°C

Shear Strength

Lap Shear Strength, N/mm ² :	
Anodized Aluminum	22
Polycarbonate	14

TYPICAL ENVIRONMENTAL RESISTANCE

Sample cured 24 hours @ 22°C

Lap Shear Strength, ISO 4587, AnAl

Chemical/Solvent Resistance

Aged under conditions indicated and tested at 22 °C

Environment	°C	% of initial strength	
		500 h	100 h
Air	65	90	85
Air	100	95	70
Air	175	60	70
95% RH	65	95	95
Water	87	85	75

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Mixing

1. LOCTITE HDD 8150NS is typically applied either with the use of meter mix equipment or directly out of cartridges through static mix nozzles. These methods of application ensure that component A and B are dispensed and mixed at the proper ratio. When properly mixed, LOCTITE HDD 8150NS should achieve a uniform color.
2. When dispensed in a large mass, heat buildup during and after mixing is normal. To reduce the likelihood of an exothermic reaction or excessive heat buildup, mix less than 100 grams at a time. Mixing smaller amounts will minimize heat buildup.

Application

1. For best performance, surfaces should be clean and residue free prior to adhesive application.
2. To assure maximum bond strength, surfaces must be mated within the adhesive's open time.
3. Use enough material to completely fill the joint when parts are clamped.

STORAGE

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 2 to 8 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{N/mm}^2 = \text{MPa}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{ft}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3