

## **WEVO-Casting Resin PD 52**

---

Two-component encapsulating system based on polyurethane. The resin component is formulated with mineral fillers.

This highly flexible system exhibits outstanding chemical resistance against most common acids and alkali solutions and an excellent flexibility at low temperatures.

The product processes a very low and stable dielectric constant over a wide variety of frequencies and broad temperature range. Additionally it shows very good adhesion to most plastic materials, metals and glass.

Temperature range of use: -60°C to +125°C .

The casting resin is used with **WEVO-Hardener 385**

Applications: Encapsulation and coating of pressure sensitive electrical and electronic components, e.g. sensors and SMD-equipped PCBs.

### Product Specification:

<u>Mixing ratio:</u>	by weight: 100 parts Casting Resin PD 52 26 parts Hardener 385		
<u>Viscosity (22°C):</u>	Casting Resin PD52:	7.000 -	9.000 mPa·s
	Hardener 385:	15 -	35 mPa·s
	Mixture:	1.200 -	2.000 mPa·s
<u>Density (22°C):</u>	Casting Resin PD52:	1,06 -	1,09 g/cm³
	Hardener 385:	1,20 -	1,24 g/cm³
<u>Colour:</u>	Casting Resin PD52:	black or as requested	
	Hardener 385:	yellowish	
<u>Potlife (200g):</u>	35 - 40 minutes	at room temperature	
	The curing time depends on the temperature, the potlife, the thickness of the layer and the casting volume.		
<u>Curing time:</u>	2 - 8 hours	at room temperature	
<u>Final hardness:</u>	14 days	at room temperature	

*It is possible to accelerate the potlife and curing time as requested.*

## **Physical Properties:**

<u>Shore-Hardness A:</u>	75 - 80	ISO 868, DIN 53505
<u>Tensile strength:</u>	9 N/mm <sup>2</sup>	ISO 527-2
<u>Elongation at break:</u>	210 %	ISO 527-2
<u>Modulus of elasticity:</u>	15 N/mm <sup>2</sup>	ISO 527-2
<u>Thermal conductivity:</u>	0,3 W/m·K	ISO 8894
<u>Glass transition temperature:</u>	-60 °C	TMA
<u>Coefficient of Expansion:</u>	65 ppm/K 175 ppm/K	< -70°C, TMA > -60°C, TMA
<u>Thermal class:</u>	E	IEC 60085
<u>Shrinkage after curing:</u>	0,6 %	
<u>Water absorption:</u>	0,5 %	after 30 days immersion
<u>Flammability classification:</u>	HB	UL94

## **Electrical Properties:**

<u>Dielectrical strength:</u>	23 kV/mm	IEC 60243-1 VDE 0303, TI.2
<u>Volume resistance:</u> 23°C/50% r.h.	$4 \cdot 10^{14} \Omega \cdot \text{cm}$	IEC 60093 VDE 0303, TI.30
<u>Surface resistance:</u> 23°C/50% r.h.	$> 10^{16} \Omega$	IEC 60093 VDE 0303, TI.30
<u>Dielectric constant <math>\epsilon</math>:</u> at 50 Hz, 23°C bei 10 kHz, 23°C bei 1 MHz, 23°C	3,0 2,95 2,98	IEC 60250 VDE 0303, TI.4
<u>Dissipation factor tan <math>\delta</math>:</u> at 50 Hz, 23°C bei 10 kHz, 23°C bei 1 MHz, 23°C	0,08 0,06 0,07	IEC 60250 VDE 0303, TI.4
<u>Comparative tracking index:</u>	CTI 600	IEC 60112 VDE 0303, TI.1

Packaging: 5 kg, 10 kg and 30 kg-buckets 250 kg drums

Shelf life: in original closed cans or drums, dry storage between 15°C and 25°C, 6 months.

## **Storing conditions for WEVO-Hardener 385:**

WEVO-Hardener 385 should be stored at +20°C to +25°C. Lower storage temperatures (15°C) should be avoided due to possible crystallisation. For the same reason the hardener has to be protected against freeze.

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and therefore, entirely your own responsibility. Should in spite of this, liability be established by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.