



LOCTITE® ECCOBOND UF 9000AE

November 2024

PRODUCT DESCRIPTION

LOCTITE® ECCOBOND UF 9000AE provides the following product characteristics:

Technology	Epoxy
Appearance	Black liquid
Product benefits	• High purity • Low CTE • Low die warpage • Good flow • Self-filleting • Optimized viscosity and modulus • Low resin bleed out (RBO) performance • 260°C reflow capability for Pb-free, low-k applications
Cure	Heat cure
Application	Semiconductor underfill; Electronic encapsulant
Typical application	Flip chip BGA and Cu pillar

LOCTITE® ECCOBOND UF 9000AE liquid epoxy underfill encapsulant is designed for large die flip chip BGA and Cu pillar package applications requiring low thermal expansion, fast capillary flow and long worklife.

When fully cured, LOCTITE® ECCOBOND UF 9000AE forms a rigid, self-filleting, protective seal that dissipates stress in solder joints extending electrical, thermal and moisture reliability performance.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield, CP 51, 25°C, mPa.s (cP)	
Speed 5 rpm	9,082
Thixotropic index (0.5/5 rpm)	0.85
Specific gravity @ 25°C	1.71
Pot life @ 25°C, hours	24
Shelf life @ -40°C, days	365

TYPICAL CURING PERFORMANCE

Recommended cure condition

- 15 minute ramp to 100°C; 90 minute hold @ 100°C
- + 15 minute ramp from 100°C to 165°C; 2 hour hold @ 165°C

The above cure profiles are guideline recommendations. These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical properties

Coefficient of thermal expansion, ppm/°C:	
Below Tg	23
Above Tg	85
Glass transition temperature, °C	
by DMA	111
by TMA	112
Storage modulus, DMA, N/mm²	
@25°C	13,500
@250°C	136

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

Thawing

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. Thaw times are listed as follows:
 - 10 cc syringes = 1 hour
 - 30 cc syringes = 1.5 hours
 - 55 cc syringes = 2 to 3 hours
 - 6 oz cartridges = 4 to 5 hours
4. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
5. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.



Directions for use

1. While not essential, the underfill area should be cleaned of contaminants and obstructions to optimize the speed and quality of the underfill.
2. Thawed adhesive should be immediately placed on dispense equipment for use.
3. For best performance, adhesive should be completely used within the product's recommended work life.
4. The substrate should be pre-heated prior to dispensing to ensure even underfill flow under the die. The preheating time depends on the thermal mass and the heating method. Using a thermocouple to measure the actual temperature on top of the substrate near the dispense area is recommended. The recommended substrate temperature is typically 90 to 100°C.
5. The underfill volume depends on several factors including die size, gap height, bump density, and fillet height. Dispense pattern will primarily depend on bump layout and die size. Dispensing optimization may be necessary to produce void-free parts. A 60-80% line (1 to 3 passes) centered along the die size is generally recommended.
6. Minimal delay time between passes is recommended to avoid underfill overflow on top of the die (0 to 20 seconds). The recommended needle size is typically 22 to 25 gauge.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40°C. Storage greater than -15°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{MPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.



Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2

For the most direct access to local sales and technical support visit: <https://www.henkel-adhesives.com>